

Glass pearls

Fine sand: 0,6 – 0,8 mm
Filtration media: Glass pearl
Backwash rate: 16 m³/hr/m²
Effective size (mm): 0,61
Uniformity Coefficient: 1,21
Bulk Density: 1,61
Mohs hardness: 7,0

Chemical compositions	
Silicon dioxide (SiO ₂)	70.00 – 75.00 %
Sodium oxide (Na ₂ O)	12.00 – 15.00 %
Calcium oxide (CaO)	7.00 – 12.00 %
Magnesium oxide (MgO)	+/- 5.00 %
Aluminium (Al ₂ O ₃)	+/- 2.50 %
Potassium oxide (K ₂ O)	+/- 1.50 %